



## TECANAT™ TECANAT™ GF20

TECANAT™ is a natural unfilled polycarbonate that has transparency, excellent impact strength and tensile properties. TECANAT™ GF20 is a 20% glass-reinforced polycarbonate with higher temperature and tensile properties

than the unfilled TECANAT™.

Polycarbonate is an amorphous thermo-plastic. Good electrical properties combined with superior impact strength and moderate chemical resistance make this product

widely accepted for numerous applications. This product is offered in many popular rod and plate sizes.

- **Superior impact strength**
- **Outstanding mechanical strength and stiffness**
- **Excellent dimensional stability**
- **Good electrical properties**
- **Transparency**
- **Good machinability**

Plastic & Metal Center, Inc.  
23162 La Cadena Drive  
Laguna Hills, CA 92653  
Tel: 949-770-8230  
[www.plastic-metal.com](http://www.plastic-metal.com)

*Typical applications include business equipment where gears, rollers, internal mechanical parts, connectors and relays are required. The automotive industry uses polycarbonate materials for pumps, valves, light bezels and instrument panels. It also is applicable to many other industries.*

# TYPICAL PROPERTY VALUES

	PROPERTIES	ASTM Test Method	Units	TECANAT™	TECANAT™ GF20
<b>PHYSICAL</b>	Density	D792	lbs/in <sup>3</sup>	0.0430	0.0434
	Specific Gravity	D792	g/cc	1.19	1.2
	Water Absorption, @ 24 hours, 73°F	D570	%	0.15	0.16
	@ Saturation, 73°F	D570	%	0.35	0.29
<b>MECHANICAL</b>	Tensile Strength @ Yield, 73°F	D638	psi	8,000	16,000
	Tensile Modulus	D639	psi	300,000	860,000
	Elongation @ Break, 73°F	D638	%	50	5
	Flexural Strength, 73°F	D790	psi	14,200	19,000
	Flexural Modulus, 73°F	D790	psi	340,000	798,000
	Compressive Strength	D695	psi	-	-
	Izod Impact Strength, 73°F	D256	ft-lbs/in	1.7	2.06
	Rockwell Hardness, 73°F	D785	M (R) Scale	70 (118)	-
	Shure Hardness	-	D Scale	-	-
	Wear Factor Against Steel, 40 psi, 50 fpm	D3702	in <sup>3</sup> x $\frac{1}{hr}$ PV	2500 x 10 <sup>-10</sup>	120 X 10 <sup>-10</sup>
	Static Coefficient of Friction	D3702	-	-	-
	Dynamic Coefficient of Friction, 40 psi, 50 fpm	D3702	-	0.38	0.22
	<b>THERMAL</b>	Heat Deflection Temperature @ 66 psi	D648	°F	280
@ 264 psi		D648	°F	270	295
Coefficient of Linear Thermal Expansion		D696	in/in/°F	3.8 x 10 <sup>-5</sup>	1.5 X 10 <sup>-5</sup>
Maximum Servicing Temperature, Intermittent		-	°F	275	270
Long Term		UL746B	°F	240	266
Specific Heat		-	BTU/lb-°F	0.30	-
Thermal Conductivity		-	-	1.32	-
Vicat Softening Point		-	°F	310	329
Melting Point		D2133	°F	-	-
Flammability	UL94	-	HB	-	
<b>ELECTRICAL</b>	Surface Resistivity	D257	ohm/square	-	-
	Volume Resistivity	D257	ohm-cm	1.0 x 10 <sup>17</sup>	1.0 x 10 <sup>17</sup>
	Dielectric Strength	D149	V/mil	380	490
	Dielectric Constant, @ 60 Hz, 73°F, 50% RH	D150	-	3.2	3.17
	@ 1 MHz	D150	-	2.96	3.13
	@ 20 GHz	D150	-	-	-
	@ 30 GHz	D150	-	-	-
	Dissipation Factor, @ 60 HZ, 73°F	D150	-	0.0009	0.0009

This information is only to assist and advise you on current technical knowledge and is given without obligation or liability. All trade and patent rights should be observed. All rights reserved. Data obtained from extruded shapes material. TECANAT™-Ensinger Ind.

## MATERIAL AVAILABILITY

**Rods:** Diameters: 3/16" to 4-3/4" thickness, 10' length  
5" and greater thickness, 5' length

**Plates:** 1/4" to 4" thickness inclusive are 2' x 4'

## Primary Specification (Resin) (Typical)

**TECANAT™:** ASTM-D-3935 PC0110B34720

**TECANAT™ GF20:** ASTM-D-3935 PC0110G20A00000

## Shapes Specification (Typical)

ASTM-D-6098 S-PC0110

ASTM-D-6098 S-PC0100G20

**Profiles, tubes, and special sizes are custom-produced on request.**



**ENSINGER-HYDE**

ASK. THINK. SUCCEED.



Division of Ensinger, Inc.

HEADQUARTERS  
365 Meadowlands Boulevard  
Washington, Pennsylvania 15301

**Telephone:** 800-243-3221 Sales  
800-869-4029 Technical  
**Fax:** 724-746-9209

e-mail: sales@ensinger-ind.com

CANADA  
Ensinger-Plastifab  
8115 Lafrenais Street  
Montreal, Quebec H1P 2B1

**Telephone:** 514-325-9840  
**Fax:** 514-325-5222

Web site: www.plastifab.ca  
E-mail: infoprod@plastifab.ca

DISTRIBUTED BY

Plastic & Metal Center, Inc.  
23162 La Cadena Drive  
Laguna Hills, CA 92653  
Tel: 949-770-8230  
www.plastic-metal.com